TECHNICAL DATA SHEET



CBE417 Blown Stretch Film

| Product description | Stretch wrap film for manual use, on extended core |
|-------------------------------|--|
| Product data | |
| ~ raw material | LLDPE |
| ~ colour | blue tint |
| ~ roll width | 400mm |
| ~ roll width tolerance | -0mm/+5mm |
| ~ roll length | 300mtr |
| ~ roll length tolerance | +/- 2.0% |
| ~ film thickness | 17mu |
| ~ film thickness tolerance | -10/+0% |
| ~ kinetic C.O.F. | 0.400 - 0.721 (ASTM D1894-14) |
| ~ static level | max. 15kV (715 static meter) |
| ~ impact strength (drop dart) | 2 (ASTM D1709-04) |
| ~ nominal density | 0.918g/cm³ |
| ~ yield | 6.24g/lm |
| | 64.08m²/kg |
| ~ outside diameter | 92mm (target) |
| ~ core type | cardboard |
| ~ core inside diameter | 38mm |
| ~ core outside diameter | 46mm |
| ~ core length | 580mm |
| Packing data | |
| ~ rolls per case | 6 |
| ~ total case weight | 15.6kg |
| eccai cacc ivergine | .516.15 |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |

All information and recommendations are provided to the best of our knowledge, on the basis of our practical experience.

Nevertheless we can make no warranties, expressed or implied, including but not limited to any implied warranty of merchantability or fitness for a particular purpose.

The user is therefore responsible for determining whether the product is fit for a particular purpose and suitable for the user's method of application.