## TECHNICAL DATA SHEET



## EBP48 Buff Polypropylene Tape

Product description	Standard packaging tape for general manual packaging applications
Technical data	
~ backing material	bi-axial oriented polypropylene film
~ film thickness	23mu (ASTMD 3652)
~ adhesive	pressure sensitive water based acrylic
~ coating weight	15gsm (ASTMD 3652)
	note: +/- 6% on coating thickness is acceptable)
~ initial tack	4.52cm (ASTMD-3121M)
~ peeling αdhesion	6.1N/inch (ASTMD-3330M)
~ shear value on steel	> 24 hours (ASTMD-3654M)
~ tensile strength	100.0N/inch (ASTMD-3759)
~ elongation at break	110% (ASTMD-3759)
~ application temperature	15°C - 65°C
Storage data	
~ optimum storage time	maximum 6 months
~ optimum temperature	22°C
~ optimum humidity	0.5RH
~ protect from	extreme temperature, extreme humidity and direct sunlight
Packaging data	
~ rolls per case	36
~ case weight	5.8 kg