TECHNICAL DATA SHEET



ECP48 Clear Polypropylene Tape

Product description	Standard BOPP packaging tape for general manual packaging applications
Technical data	
~ backing material	bi-axial oriented polypropylene film
~ film thickness	23mu (ASTMD 3652)
~ adhesive	pressure sensitive water based acrylic
~ coating weight	15gsm (ASTMD 3652)
	note: +/- 6% on coating thickness is acceptable)
~ initial tack	4.52cm (ASTMD-3121M)
~ peeling adhesion	6.1N/inch (ASTMD-3330M)
~ shear value on steel	> 24 hours (ASTMD-3654M)
~ tensile strength	100.0N/inch (ASTMD-3759)
~ elongation at break	110% (ASTMD-3759)
~ application temperature	15ºC - 65ºC
Storage data	
~ optimum storage time	maximum 6 months
~ optimum temperature	22°C
~ optimum humidity	0.5RH
~ protect from	extreme temperature, extreme humidity and direct sunlight
Packaging data	
~ rolls per case	36
~ case weight	5.8 kg
-	

All information and recommendations are provided to the best of our knowledge, on the basis of our practical experience.

Nevertheless we can make no warranties, expressed or implied, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is therefore responsible for determining whether the product is fit for a particular purpose and suitable for the user's method of application.